

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
27 January 2005 (27.01.2005)

PCT

(10) International Publication Number  
**WO 2005/007729 A1**

(51) International Patent Classification<sup>7</sup>: C08J 9/00

(21) International Application Number:  
PCT/US2004/021173

(22) International Filing Date: 30 June 2004 (30.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/485,292 7 July 2003 (07.07.2003) US

(71) Applicant (for all designated States except US): DOW  
GLOBAL TECHNOLOGIES INC. [US/US]; Washing-  
ton Street, 1790 Building, Midland, MI 48674 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): MARTINEZ, Felipe  
[CO/US]; 3206 Loblolly Pines Way, Houston, TX 77082  
(US).

(74) Agent: DICKERSON, James, H.; The Dow Chemical  
Company, Intellectual Property, P.O. Box 1967, Midland,  
MI 48641-19677 (US).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: THIN FOAMED POLYETHYLENE SHEETS

(57) Abstract: The present invention relates to the use of particular blends of LLDPE and LDPE together with specific fabrication conditions to make foamed sheets of thin gauge with MD tear properties similar to an equivalent gauge non-foamed sheet of the same composition. In particular, blends which combine a high MI LLDPE rich fraction with a low MI branched LDPE minor fraction provide the adequate balance of mechanical strength of the polymer base with its melt strength, extensibility and stress relaxation, allowing a thin foam film with MD tear strength which is comparable to non foamed counterparts of similar gauge and composition. The foamed films of the present invention are thin (generally from about 1 to 10 mils thick), and have an MD tear strength of at least about 160 grams for a 3 mil film as measured by ASTM D 1922. The foamed films of the present invention are preferably made at least in part from blends which comprise from 10 to 95 percent by weight of LLDPE having a relatively high (1.5 to 6) MI and from 5 to 90 percent of an LDPE resin having a relatively low MI (0.5 to 2.0).



WO 2005/007729 A1